

## POLYURETHANE TURF SEAM ADHESIVE OPERATING INSTRUCTIONS TWO-COMPONENT DISPOSABLE KIT

FOR PROFESSIONAL USE ONLY



## **SET-UP TEMPERATURES & PERSONAL PROTECTIVE EQUIPMENT (PPE)**





Typically, chemical should be between 60–90°F (16–32°C). See TDS for formula temperature recommendations.

Wear protective glasses with sideshields or goggles, nitrile gloves, and clothing that protects against dermal exposure. Recommend using in a well ventilated area with certified respiratory protection or a powered air purifying respirator (PAPR). See SDS (available at www.californiasportssurfaces.com).

## SET-UP PROCEDURE FOR SINGLE-PACKAGE TWO-COMPONENT MODEL



 Shake kit for 1–2 minutes before use to ensure proper mixing. Typically, chemical should be between 60–90°F (16–32°C). See TDS for formula shaking and temperature recommendations.



2. Push in top of panel to open. Pull down flap for dispensing unit hose assembly. Remove nozzle packet and read instructions.



3. Open top flap of box to expose cylinder valves. Extend attached dispensing unit hose assembly.



4. Open the valves completely by turning the valves COUNTER CLOCKWISE. Top flap may be removed or left in place during use or storage.

## SET-UP PROCEDURE FOR DUAL-PACKAGE TWO-COMPONENT MODEL



 Shake each cylinder for 1–2 minutes before use to ensure proper mixing, see TDS for formula shaking and temperature recommendations on these instructions. Chemical should be between 60–90°F (16–32°C).



2. Thread red coded hose to A-component cylinder and black coded hose to B-component cylinder and tighten with supplied 9/16" wrench.



3. Open the valves completely by turning the valves COUNTER CLOCKWISE. Cylinder valves must be upright during use.

## **ATTACHING A NOZZLE TO HANDI-GUN® DISPENSING UNIT**



 Before attaching nozzle, use petroleum jelly on face of gun. This is used to help keep the gun face clean from cured foam or contamination that could block one of the chemical ports.



- 2. Insert bottom tab of nozzle into bottom slot of dispensing unit.
- 3. Attach top latch by pushing towards back of unit, until an audible "snap" is heard.



- 4. Unit is ready to use.
- 5. After attaching nozzle, spray into "test shot" receptacle.
- 6. To remove used nozzle, push top latch up and forward to unsnap.

## **SPRAYING FOAM**

- 1. Wear protective glasses with sideshields or goggles, nitrile gloves, and clothing that protects against dermal exposure. Recommend using in a well ventilated area with certified respiratory protection or a powered air purifying respirator (PAPR). See SDS (available at www.californiasportssurfaces.com).
- For best results, use when material is between 70–85°F (21–29°C), see TDS for formula specific temperature recommendations. Clean grease, oil, dirt and water off surfaces to be foamed. Shake kit before use for one (1) to two (2) minutes depending on the product requirements (See TDS for more information). For large kits, thread hose to cylinder until hand tight then tighten with supplied 9/16" wrench.
- 3. Fully open both cylinder (A & B) valves.
- 4. Attach nozzle to the dispensing unit; use of enclosed petroleum jelly on the face of the dispensing unit before attaching nozzle will help prevent contamination by cured foam or chemical and help keep the sealing ports clean. (Detailed instructions for attaching nozzle shown in previous section.)
- 5. When spraying the dispensing unit for the first time and with each new kit, dispense foam by squeezing the trigger only 1/2 to 3/4 open until desired output is achieved. This controllable metering is a major advantage of the dispensing unit, allowing the user complete control of the flow rate that best suits the application.
- 6. Once the trigger is released it **MUST BE REACTIVATED WITHIN 30 SECONDS** or a new nozzle must be installed. Failure to do this could result in chemical leakage, spills or splashes which can ruin the dispensing unit and/or hoses.
- 7. IMPORTANT: After releasing trigger, activate the trigger safety to prevent accidental discharge.
- 8. All dispensing unit nozzles are easily cleanable and solvent resistant. To clean nozzles, liquid chemical must be dissolved prior to its complete chemical reaction by flushing the nozzle with a suitable solvent such as Sport Tough Multipurpose Cleaner. Gun face can be kept clean with the use of petroleum jelly on the face or with a soft cloth to remove residue.
- 9. Do not remove hoses from cylinders. Do not flush/clean hoses with air, water or solvent. Removing and/or cleaning hoses may compromise the foam.

## **IMPORTANT APPLICATION NOTES**

- 1. Actual yields will vary depending on factors such as ambient conditions, application technique, foam density, etc. See Technical Data Sheet for additional information.
- 2. Suitability of this product for any particular purpose, such as achieving desired structural properties, performance specifications or application requirements must be determined by the end user, prior to use. Verification that product is properly applied and installed is also the responsibility of the end user.

## **STORAGE & REUSE**

- 1. Close cylinder valves.
- Do not store full cylinders at temperatures above 100°F (38°C) (partial or used cylinders above 90°F [32°C]) (or below 60°F (16°C). Kits stored below 70°F must be given sufficient time (1-2 days) for the chemical to warm up to 60–90°F (16–32°C), see TDS for formula specific temperature recommendations.
- 3. The used nozzle should be left on the dispensing unit during storage in order to help keep the outlet ports of the dispensing unit clean and free from any dust, dirt or chemical that can affect the proper sealing of the nozzle. **SAFETY:** Always engage the trigger safety and close all supply valves during storage.
- 4. All dispensing unit nozzles are easily cleanable and solvent resistant. To clean nozzles, liquid chemical must be dissolved prior to its complete chemical reaction by flushing the nozzle with a suitable solvent such as Sport Tough Multipurpose Cleaner. Gun face can be kept clean with the use of petroleum jelly on the face or with a soft cloth to remove residue.
- 5. Do not remove hoses from cylinders. Do not flush/clean hoses with air, water or solvent. Removing and/or cleaning hoses may compromise the foam.

#### TO REUSE DISPENSING UNIT AFTER STORAGE:

- 1. Remove the used nozzle.
- 2. Check the face of the dispensing unit to make sure the outlet ports are clear and the face of the unit is free from dirt, chemical or other debris. If necessary, use a soft cloth or rag to remove any cured foam or chemical from the face of the dispensing unit. Use of enclosed petroleum jelly is recommended to cover the face of the unit in order to prevent further contamination or if chemical is accidentally leaked into this area.
- 3. Shake kit or cylinders for 1-2 minutes to ensure proper mixing. Typically chemical should be between 60–90°F (16–32°C). See TDS for formula specific shaking and temperature recommendations.
- 4. Fully open all supply valves.
- 5. Dispense into waste containter to verify that both chemicals are being dispensed in approximately equal streams.
- 6. The dispensing unit is a disposable unit not designed for prolonged storage or continuous re-use. To help extend the storage life, it is recommended to dispense a minimal amount of foam from unit at least **once every three (3) days** to ensure optimum flow of chemical through hoses. **Use of contents within 30 days of initial use is recommended.**

## **EFFECTS OF TEMPERATURE**

- Proper temperature plays a critical role in the performance of any two-component polyurethane foam system. Both the liquid chemical temperature and the ambient temperature (i.e. mold temperature) will affect system performance.
- Recommended chemical temperature is 60–90°F (16–32°C), see TDS for formula specific temperature recommendations. If the chemicals are not at the proper temperature, they may dispense in an improper ratio, thereby leading to poor quality foam. Please see Technical Data Sheets (TDS) for specific formulation temperature requirements.
- NOTE: It may take from several hours to several days (in the case of the larger systems) for the chemical temperature to reach the proper temperature. This is especially true if the product has been recently shipped or stored in colder temperatures.

## HANDLING EMPTY / PARTIALLY EMPTY DISPOSABLE CYLINDERS

- 1. DO NOT INCINERATE CYLINDERS.
- 2. Empty cylinders by dispensing the foam into a waste container like a cardboard box or plastic bag. Depressurize the used cylinders using the dispensing unit with a new nozzle attached. Spray the foam until one of the components/cylinders no longer sprays chemical.
- 3. Remove the nozzle and then continue to depressurize by dispensing the remaining chemical(s) into a waste container (a box lined with a plastic bag) that has adequate industrial liquid absorbing medium in the bottom. Dispense the residual chemicals until the pressure is down to a minimum or there are just large bubbles in the hose.
- 4. Close the cylinder valves completely, and then operate the dispensing unit again to empty and depressurize the hoses. Use a 9/16" wrench and remove the hoses from the cylinders. Use caution in case there is some residual chemical and/or pressure in the hoses.
- 5. Invert the cylinder and point away from face. Slowly open the cylinder over the waste container to catch any residual spray.
- 6. Return the cylinder to an upright position. Shake the container; there should not be any sloshing of liquid. Make sure to leave valves OPEN-do not close. DO NOT PUNCTURE.
- 7. The user of this material has the responsibility to dispose of empty cylinders, unused material and residues in compliance to all applicable federal, state, international and local regulations regarding the treatment, storage, and disposal for hazardous and nonhazardous wastes. Check with your local waste disposal service for guidance.
- 8. NOTE: After dispensing if one cylinder has chemical left in it, treat as hazardous material.

## **TROUBLESHOOTING GUIDE**

Equivalent flow of both A-component and B-component is required with all two-component polyurethane systems in order to obtain proper performance, curing and optimum yields. If a problem occurs, the cause is typically due to uneven chemical flow that is caused by a blockage of one of the chemicals.\*

PROBLEM	POSSIBLE CAUSE	SOLUTION
Poor chemical flow	Cylinder valves not fully open	Turn cylinder valves counter-clockwise until they stop
	Cylinder valves in incorrect position	Place cylinder valves in upright position
	Material is too cold	Chemical temperature must be between 70–85°F (21–29°C)
Foam leaking from hose connections	Hoses not tightened	Tighten all hose fittings
	Cross-threaded hose	Replace gun hose assembly
Dark crunchy foam/ off-ratio (A-rich)	Material is too cold	Chemical temperature must be between 70–85°F (21–29°C)
	Clogged nozzle	Replace nozzle
	Blockage of one chemical port	Clean gun face and apply petroleum jelly
	Gun crossover	Replace hose
White spongy or shrinking foam/ off-ratio (B-rich)	Material is too cold	Chemical temperature must be between 70–85°F (21–29°C)
	Clogged nozzle	Replace nozzle
	Blockage of one chemical port	Clean gun face and apply petroleum jelly
	Gun crossover	Replace hose
Sputtering from nozzle	Cylinders are empty	Switch to new kit
	Clogged nozzle	Replace nozzle
	Hose blockage	Replace hose

\*If kit is still not fully operational, stop spraying and contact the distributor where purchased.



With the nozzle removed, check that both chemicals flow with equivalent force.



Partial or complete blockage of one chemical port will result in off-ratio foam.

\*Handi-Gun<sup>®</sup> being shown for reference only.

## SPORT TOUGH MULTIPURPOSE CLEANER

All Handi-Gun<sup>®</sup> nozzles are easily cleanable and solvent resistant. To clean nozzles, liquid chemical must be dissolved prior to its complete chemical reaction by flushing the nozzle with Sport Tough Multipurpose Cleaner or other suitable solvent. Gun face can be kept clean with the use of petroleum jelly on the face or with a soft cloth to remove residue. **Cleaning a nozzle more than twice is not recommended.** 

## WARNINGS

Sport Tough Adhesive products are composed of a diisocyanate, hydrofluoroolefin blowing agent amine catalyst and polyol. Consult the product's SDS (available at www.californiasportssurfaces.com) for specific information. The urethane foam produced from these ingredients will support combustion and may present a fire hazard if exposed to a fire or excessive heat about 240°F (116°C). Wear protective glasses with side shields or goggles, nitrile gloves, and clothing that protects against dermal exposure. Recommend using in a well ventilated area with certified respiratory protection or a powered air purifying respirator (PAPR). For more information regarding a certified respiratory program please visit http://www.cdc.gov/niosh/. To view or receive a copy of ICP Building Solutions Group's respirator program, please contact ICP Building Solutions Group Customer Care at 800-321-5585. Personal Protective Equipment can be purchased through ICP Building Solutions Group distribution by purchasing a Contractor Safety Kit (F65251). The Contractor Safety Kit includes: nitrile gloves, contractor safety glasses, and a NIOSH approved negative pressure half mask respirator. For professional use only.

**WARNING:** Non-flammable compressed gas. Keep away from heat. Smoking and open flames, including hot work, should be prohibited in the vicinity of a foaming operation. Avoid contact with skin and eyes. May cause sensitization by inhalation and/or direct skin contact. Avoid prolonged or repeated breathing of vapor. **KEEP OUT OF REACH OF CHILDREN. FIRST AID:** In any first aid case CONSULT A PHYSICIAN. **EYES:** Flush with water for at least 15 minutes. **SKIN:** Remove contaminated clothing. Wash skin with plenty of soap and water. Cured foam must be removed manually. **INHALATION:** If breathing is difficult, give oxygen. If breathing has stopped, give artificial respiration. **INGESTION:** give large quantities of water. Do NOT induce vomiting. Contact a physician immediately in any first aid situation. Consult the product's SDS (available at www.californiasportssurfaces.com) for specific information.

## IMPORTANT

Always read all operating, application and safety instructions before using any products from ICP Building Solutions Group Use in conformance with all local, state and federal regulations and safety requirements. Failure to strictly adhere to any recommended procedures and reasonable safety precautions shall release ICP Building Solutions Group of all liability with respect to the materials or the use thereof. For additional information and location of your nearest distributor, call ICP Building Solutions Group 330-753-4585.

**NOTE:** Physical properties shown are typical and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal conditions and may vary upon use, temperature and ambient conditions. Right to change physical properties as a result of technical progress is reserved. This information supersedes all previously published data. Yields shown are optimum and will vary slightly depending on ambient conditions and particular application. Read all product directions and safety information before use. This product is organic, and therefore, is combustible. Consult local building codes for specific requirements regarding the use of cellular plastics or urethane foam in construction.



# For more information, visit www.californiasportssurfaces.com

FOR PROFESSIONAL USE ONLY