



WIPE-OUT STAIN BLOCKER

DESCRIPTION:

Wipe-Out Stain Blocker is a concentrated acrylic latex stain blocking primer that provides exceptional adhesion and stain blocking properties as a preparation for the installation of athletic surfaces. Wipe-Out is intended to impede the migration of most bleeding stains on new asphalt or concrete surfaces, as well as existing acrylic surfaces.

APPLICATION:

50-70 durometer rubber squeegee

DRYING TIME:

Approximately 2 hours for each coat

COLOR RANGE:

Black (4203)

APPLICATION SPECIFICATIONS

Wipe-Out Stain Blocker can be applied over new or existing asphalt or concrete surfaces that have a sound base of adequate thickness and stability. Existing surfaces should have good drainage and be free from cracks and depressions.

SURFACE PREPARATION

Allow new asphalt to cure a minimum of 14 days and new concrete to cure for a minimum of 28 days. Do not allow the use of curing agents. Concrete surface must have at least a medium-broom finish profile and new concrete must be acid-etched with either phosphoric or muriatic acid and Ti-Coat epoxy before the application of Acrylic Resurfacer.

The entire surface must be free of dirt and debris. Pressure washing may be needed.

It is recommended that any low spots or depressions be patched and leveled prior to the application of surfacing materials.

Wipe-out Stain Blocker is not intended to replace any coats within a specified system. For new surfaces, a filling coat of CSS Acrylic Resurfacer is necessary to give you a uniform surface before the Wipe-Out Stain Blocker. If surface texture necessitates a 2nd coat of Acrylic Resurfacer, then both coats should still be applied before proceeding with the Wipe-Out.

MIXING

Wipe-Out Stain Blocker is ready to use from the drum. Some light mixing may be necessary, but **do not dilute and do not add sand**. Wipe-Out Stain Blocker shall be applied to obtain a coverage rate of 0.04-0.06 gallons per square yard (0.18-0.2 liters per square meter) per coat. In extreme cases, a second coat may be necessary. No application shall be covered by a succeeding application until thoroughly cured.

Application methods:

- Use a 50-70 durometer rubber squeegee to level material across the court.



- After initial pour, acrylics should not be poured onto dry surface. Pour additional materials into existing wet window.
- Care should be taken not to leave ridges where adjoining applications overlap.
- Under hot conditions, application is improved by keeping surface damp with a fine mist water spray. Do not allow water to puddle.

LIMITATIONS:

Apply only when ambient surface and air temperature are a minimum 50°F (10°C) and rising.

Do not apply when rain or high humidity is imminent.

The surface should be sound, free of cracks and deterioration.

The surface should be clean of all contaminants.

Wipe-Out Stain Blocker will not prevent cracks from occurring or reoccurring.

Keep from freezing.

Do not store in the direct sunlight.

Once opened, entire contents should be used.

Shaded and Indoor areas will dry more slowly.

Wipe-Out Stain Blocker is intended to mitigate stain migration, but it is NOT a waterproofing material.