

REBOUND ACE HSA

REPAIR SPECIFICATION

Delamination Areas (Blistered areas between coating layers)

The following outlines the steps to be taken and products used in the repair of any delamination areas/damaged areas in Rebound Ace HSA surfaces.

Step 1 Grind 'Delaminated' Areas

With an angle grinder (small wheel) carefully remove delaminated areas. Remove as little depth of base (binder/rubber) layer as possible. Feather edges, using finer grade abrasive paper by hand.

If delaminated/blistered areas expose the rubber base layer, then these areas must be sealed using, Mat Sealer PU or proprietary polyurethane sealant. (Should the rubber mat itself be damaged, please consult Rebound Ace Sports for recommendations).

Mix carefully and ensure total weighed quantity is mixed thoroughly and all material is removed from sides of mixing vessel. Use clean plastic/steel mixing containers.

Pour/spatula in the mixed product to fill the section of exposed base layer.

Refer to separate technical bulletins for these products.

Allow the material to cure for a minimum of 4 hours, between coats. Apply a further coat if required to ensure total seal of the base layer, and to seal any bubbles in the mat sealer.

Allow to cure for 24 hours, before the Rebound Ace Tycoat coat is applied.

Step 2 Rebound Flexible Filler Coat (Green, single pack, water-based filler product)

Fill the prepared area with Rebound Flexible Filler Coat, applied by spatula or paint scraper. Two or three applications may be necessary, depending on degree of sanding. Maximum of 2mm thickness per coat.

Allow 5-6 hours minimum between coats at 23°C, good drying conditions. When damaged area has been filled to the surface level of the surrounding surface, allow the Rebound Flexible Filler Coat to cure for a minimum of 24 hours, and then sand patched area with a fine grade abrasive paper by hand to

produce a smooth even finish, ensuring the edges of the patched area are 'feathered' into surrounding surface.

Step 3 **Rebound Ultra Topcoat**

Prior to coating the surface of the court must be high pressure water blast (2500 psi) cleaned to remove all surface contamination.

Food stains, grease marks, chewing gum spots etc., must be completely removed, by using a high quality industrial grade detergent. Diluted to an appropriate strength and then thoroughly washed off the court surface.

Any areas showing rough surface texture, pimpling of the surface layer, etc. must be sanded, de-burred or repaired.

Ensure Rebound Topcoat is mixed prior to removing any of the material as supplied in the pail. Mixing is to be done with a high shear electric mixer producing a good mixing action without turbulence or air entrainment.

Blend material from different batch no.'s thoroughly, before any dilution/mixing is attempted.

Mix Ratio Rebound Ultra Topcoat is 3 parts **Rebound Ultra Topcoat** by Volume to 1 part Potable Water.

Refer to separate technical bulletin for full details of application.

Notes

The dilution of the Rebound Ultra Topcoat can be adjusted in the nominated range to allow for atmospheric conditions and court surface conditions.

The double brooming or squeegee/broom technique is to be used.

Allow 1 to 3 hours between coats, depending on atmospheric conditions.

Apply first coat across the width of the court (narrow dimension). Denib between coats to remove any foreign matter or rough surface texture left in first coat.

Apply second coat down the length of the court. Allow 1 to 3 hours depending on drying condition, before linemarking.

Allow 24 hours drying before court is used for playing, in good weather conditions. In damp, cold conditions allow longer time period, up to 72 hours.

The drying times advised in this specification are for good drying conditions, 20-25°C, and medium/low relative humidity. If rain, cold or damp conditions occur, allow additional time for drying.