

IMPACT COLOUR COAT WB (2-part PU) APPLICATION PROCEDURE

Description / Recommended Uses

Impact Colour Coat WB is a 2-part, highly durable pigmented water-based polymer topcoat. The Satin finish minimises glare and provides good traction for sports shoes. The toughness, flexibility and high abrasion resistance of **Impact Colour Coat WB** make it an ideal finish for the **Rebound Ace Impact** cushioned system designed for indoor sports, other recreation and multi-purpose uses.

The Impact Catalyst ensures exceptional adhesion to, and performance properties with Impact surfaces.

Surface Preparation

New Polyurethane Cushioned Sports Floors

Apply to polyurethane self-levelling layer which is clean and free of all dust, dirt etc. If polyurethane has been curing for more than 48 hours, lightly sand to remove gloss with 80 grit paper on mechanical sander before application. Ensure all sanding dust is removed.

Existing Polyurethane Cushioned Sports Floor

Sand surface using 60 - 80 grit paper on mechanical sander to provide a mechanical key and remove any gloss. Ensure all sanding dust, dirt etc. is removed before application of topcoat.

Application

Mix Impact Colorcoat WB with the Impact Colorcoat Catalyst (250ml per 20 litre drum) [.077 gal per 5.28 gal]. Thoroughly mix with a drill stirrer. Transfer all material into another drum, scraping the sides to ensure all material is transferred. Remix thoroughly.

Apply **Impact Colour Coat WB** using lambswool roller (approx. 12mm nap), 360mm-460mm (14-18 inches) wide, applying the material from a roller tray. Do not pour material onto floor for spreading with roller. Use an evenly wetted roller with excess material removed and apply in even strokes to a defined area, starting at the centre and working left than right until roller is spent. Then lay off coated area with spent roller starting at one side and working across the coated area. Overlap each pass by 50% to ensure an even finish, and lift roller when laying off into previously coated section in front. Ensure any excess material, ridges from roller edges, drips etc, are removed as coating progresses.

Depending on size of area, sufficient personnel should be used, in a staggered pattern, to ensure a continuous wet edge throughout the application period. Under normal indoor ambient conditions (22°C, 50% RH), wet edge time is approximately 10 minutes. A floor area of approximately 750m² would normally require 4 - 5 skilled applicators. Ensure edges against wall are cut in progressively with a paint brush at the starting wall edge and at the end of each run.

Apply the second coat next day.

NB : A MIXED DRUM OF PRODUCT HAS A “ USE “ TIME OF 24 HOURS. LEFT OVER MATERIAL FROM THE 1ST COAT CAN BE USED THE NEXT DAY. ENSURE PRODUCT IS RESTIRRED BEFORE USE.

Coverage: Apply two coats at a total application rate of 0.16 to 0.20 L/m² [.04 - .045 gal/sq.yd.]

Clean equipment with water before material dries.